


# AP 01

Test report C/23641/T01 Test 6 Spec 278  
Cavatina MDF panel, 6mm slots, 50mm Rockwool backing  
Sound absorption coefficient BS EN ISO 354: 0.90  
BS EN ISO 11654: Class A



**BS EN ISO 11654**